



The Source
for Imported &
Domestic
Vegetable Oils

TECHNICAL DATA

POLYMERIZED LINSEED OIL

<u>VALUES</u>	K6 GRADE	K8 GRADE	K10 GRADE
RELATIVE DENSITY AT 25° C	0.950-0.956	0.953-0.958	0.958
REFRACTIVE INDEX AT 25° C	1.481-1.487	1.486-1.491	1.491
ACIDITY INDEX	9.6%	11.5%	11.8%
SEDIMENT	Does Not Contain	Does Not Contain	Does Not Contain
COLOR GARDNER	5+	6	6
GARDNER VISCOSITY AT 25° C	Z1	Z3-Z4	Z5
DRYING TIME	Max 4 Days at 20°C	Max 4 Days at 20°C	Max 4 Days at 20°C

9/2013

Alnor Oil Company, Inc

70 East Sunrise Highway Suite 418
Valley Stream, NY 11581-1221

TEL: (516) 561-6146

FAX: (516) 561-6123 (sales) /5125(traffic)

Email: vegoil.source@alnoroil.com

The above data is given to the best of our knowledge for the convenience of the user. No warranty of fitness for a particular purpose is made.